


CHALLENGE 700-HT

Additive for Post-Lap/Polish Rinse and In-Process Wet Storage of Parts



Rinse/Wash Aid

Description

CHALLENGE 700-HT is a synthetic formulation developed for the rinsing and wet storage of lapped/polished parts. Used as directed, 700-HT minimizes scratching from in-process handling; protects parts from staining, and prevents hard-to-clean particles from adhering to the part surface for more effective downstream cleaning. Also recommended for the rinsing/washing of lapping plates, 700-HT removes process debris from both the plate's surface and grooves, thereby preventing the formation of iron oxide/abrasive particle aggregates that can dislodge and cause scratching.

When used for rinsing/washing polishing pads, 700-HT prevents staining, increases pad life by keeping the pore structure open and reduces the frequency of pad conditioning.

Benefits

- ⇒ Biodegradable
- ⇒ Minimizes scratching
- ⇒ Highly economical
- ⇒ Prevents staining
- ⇒ Minimizes plate/pad cleaning
- ⇒ Facilitates cleaning processes

Directions

CHALLENGE 700-HT is used at dilutions ranging from 2-3%, depending on the condition and type of lapping equipment being used and the workpiece. Evaluation should begin at 2% with deionized (DI) or tap water. It is fed into the rinse line and flooded over the lapping surface either before the parts are placed on the plate, or after lapping is completed. After the lapping plate has been lifted, 700-HT should be flooded over the surface. This breaks the surface tension between the parts and the plate, and removes any remaining swarf, which could cause scratching and complicate handling.

note: the rinse flow should be fed into a separate rinse line, otherwise the slurry will be diluted

For polishing applications follow the same dilution guidelines.

Additional Information

CHALLENGE Products are available in 5-gallon pails and 55-gallon drums, F.O.B. Bethel, Connecticut, and also include: grinding fluids, sawing fluids, suspension additives for lapping/polishing slurries and ultrasonic/megasonic detergents.

Material Safety Data Sheets available upon request.

Manufacturer: **INTERSURFACE DYNAMICS, Inc.**
Supplier: **N. BUCHER AG**, Pfadackerstrasse 9, 8957 Spreitenbach/Switzerland
Phone: ++41-56 418 19 90
Fax: ++41-56 418 19 99
<mailto:info@nbucheraq.com>